

<b>Physical Properties:</b>	
Absorption	1.83%
Density lbs/ft <sup>3</sup> (ASTM C97)	148.7
Bulk Specific Gravity (Astm C97)	2.38
Compression Strength, PSI (ASTM C170)	
Dry, Perpendicular	14,100.00
Wet, Perpendicular	17,400.00
Dry, Parallel	15,200.00
Wet, Parallel	12,300.00
Module of Rupture, PSI (ASTM C99)	
Parallel to Rift (With)	1,670

## 1. Versions:

Ashlar  
Rubble  
Fieldstone  
Blend

## 2. Geologic Designation:

Sandstone/Triassic Sandstone

## 3. Trade Names:

Bucks County Brownstone, Ashlar, Rubble,  
Fieldstone

## 4. Color Range:

Red, Salmon, Brown

## 5. Applications:

Exterior Walls, Interior Walls, Fireplace Facings,  
Retaining Walls, Patio Flagstone, Pool Decking, Wall  
Capping

## 6. Types:

Dimension Stone Veneer, Irregular and Random  
Ashlar

## 7. Sizes:

Standard Thickness 4", 6" & 8" veneer

## 8. Finishes:

Split Face

---

## Completed Projects:

*Southampton Bridge, Vincentown, NJ*  
Architect: New Jersey D.O.T.

*Buckingham Green, Buckingham, PA*  
Architect: George Donovan Associates

*Doylestown Presbyterian Church, Doylestown, PA*  
Architect: Samuel Carnthers

*Private Residence, Paramus, NJ*  
Architect: Not Available

*Newtown Municipal Building, Newtown, PA*  
Architect: Not Available

*Private Residence, Cranbury, NJ*  
Architect: Schroder/Perez, PC.