

Delaware Valley Sandstone Blend

Delaware Quarries, Inc.
6603 Route 202, P.O. Box 778
New Hope, PA 18938 (800) 533-4954



Physical Properties	
Absorption	.574%
Bulk Specific Gravity (Astm C97)	2.501
Compression Strength, PSI (ASTM C170)	
Perpendicular to Rift (against)	11,716.00
Parallel to Rift (with)	9184.00

1. Versions:

Rubble
Ashlar
Blends
Fieldstone Blend

2. Geologic Designation:

Lumberton/Stockton Sandstone, Triassic Sandstone, Pocono Sandstone

3 Trade Names:

Delaware Valley Gray Sandstone, Bucks County Sandstone, Golden Vein Sandstone

4. Color Range:

Red, Brown, Gray, Tan, Buff, Pink, Yellow

5. Applications:

Exterior Walls, Large Retaining Wall Blocks, Saw Blocks, Interior Walls, Fireplace Facings, Patio Flagstone, Pool Decking, Wall Capping

6. Types:

Dimension Stone Veneer, Irregular & Random Ashlar, Rough Squares & Rectangles

7. Sizes:

Standard Thickness 4", 6" & 8" veneer

8. Finishes:

Split Face, Natural Face

Completed Projects:

Trinity Episcopal Church, Solebury, PA
Architect: Michael Farewell

Plainfield Avenue Bridge, Berkley Heights, NJ
Architect: County Engineer - Howard Saersinger

Disney World, Orlando Florida
Architect - Disney

Warrington Municipal Building, Warrington, PA
Architect: George Donovan Associates

Private Residence, Solebury, PA
Architect: Hillier