

Physical Properties:	
Absorption	1.72%
Bulk Specific Gravity (Astm C97)	2.531
Compression Strength, PSI (ASTM C170)	
Perpendicular to Rift (against)	11,120.00
Parallel to Rift (with)	7,680.00
Chemical Properties:	
Silicon Dioxide as SiO ₂	72.98%
Iron Oxide as Fe ₂ O ₃	3.12%
Aluminum Oxide as Al ₂ O ₃	10.60%
Calcium Oxide as CaO	2.52%
Magnesium Oxide as MgO	1.57%
Sodium Oxide as Na ₂ O	4.99%

1. Versions:

- Rubble
- Ashlar
- Fieldstone
- Blends

2. Geologic Designation:

Sandstone, Triassic Sandstone, Pocono Sandstone

3. Trade Names:

Golden Vein Ashlar/Rubble/Fieldstone/Blend

4. Color Range:

Tan, Buff, Yellow, Light Pinks

5. Applications:

Exterior Walls, Retaining Walls, Interior Walls,
 Fireplace Facings, Patio Flagstone, Pool Decking,
 Wall Capping

6. Types:

Dimension Stone Veneer, Irregular & Random
 Ashlar

7. Sizes:

Standard Thickness 4", 6" & 8" veneer

8. Finishes:

Split Face, Natural Face

Completed Projects:

Church of the Advent, Hatboro, PA

Architect: Not Available

The Farm, Doylestown, PA

Architect: Not Available

Buckingham Municipal Building, Buckingham, PA

Architect: Not Available

Soverign Bank, New Hope, PA

Architect: Not Available