

<b>Physical Properties:</b>	
Absorption	.80%
Compression Strength, PSI (ASTM C170)	
Dry, Perpendicular	13,200.00
Wet, Perpendicular	8,360.00
Dry, Parallel	8,910.00
Wet, Parallel	6,800.00
Module of Rupture, PSI (ASTM C99)	
Dry	3,230.00
Wet	2,110.00

**1. Versions:**

Squares and Rectangles  
Strips  
Rubble

**2. Geologic Designation:**

Granite Schist

**3. Trade Names:**

Saw Creek Strips/Rubble/Squares & Rectangles

**4. Color Range:**

Silver, Gray, Buff

**5. Applications:**

Exterior Walls, Interior Walls, Fireplace Facings,  
Retaining Walls, Patio Flagstone, Pool Decking,  
Wall Capping

**6. Types:**

Dimension Stone Veneer, Irregular & Random  
Ashlar

**7. Sizes:**

Standard Thickness 4", 6" & 8" veneer

**8. Finishes:**

Split Face

---

**Completed Projects:**

*Private Residence, Watchung, NJ*  
Architect: Not Available

*Private Residence, Fort Washington, PA*  
Architect: Not Available

*Private Residence, Willstown, PA*  
Architect: Not Available