

Physical Properties:	
Absorption	0.91%
Density lbs/ft ³ (ASTM C97)	158.7
Bulk Specific Gravity (Astm C97)	2.63
Compression Strength, PSI (ASTM C170)	
Dry, Perpendicular	21,140.00
Wet, Perpendicular	15,670.00
Dry, Parallel	17,690.00
Wet, Parallel	14,640.00
Module of Rupture, PSI (ASTM C99)	
Dry, Perpendicular	1,730.00
Wet, Perpendicular	1,300.00

1. Versions:

Fieldstone
Landscape Boulders
Rubble

2. Geologic Designation:

Triassic Sandstone

3. Trade Names:

Stoney Mountain Fieldstone Split Face

4. Color Range:

Yellow, Buff, Hints of Black

5. Applications:

Exterior Walls, Interior Walls, Fireplace Facings,
Retaining Walls, Patio Flagstone, Pool Coping,
Pool Decking, Wall Capping

6. Types:

Dimension Stone Veneer, Irregular & Landscape
Boulders

7. Sizes:

Standard Thickness 4", 6" & 8" veneer,
Landscape Boulders

8. Finishes:

Split Face, Natural Stone

Completed Projects:

Essex Falls Country Club, Essex Falls, NJ
Architect: Not Available

Private Residence, New Hope, PA
Architect: Not Available

Private Residence, Upper Makefield, PA
Architect: Not Available

Private Residence, Upper Makefield, PA
Architect: Not Available